

AIRTECH

Technical sheet

USES

Recommended use

Windbreakers, Meshes, Over top covers

CHARACTERISTICS	VALUES		UNITS	STANDARDS
	WARP	WEFT		

GENERAL CHARACTERISTICS

Base cloth	1100 dTex PES HT 990 den			
Coating	PVC Lowick coating both side			
Finish	2 sides lacquered			
Weight	220		g/m ²	ISO 3801
Wind efficiency	87		%	XP G39-100-3
Porosity	44		%	
Width	315	315	cm	
Roll length	60	250	ml	

FABRIC RESISTANCE

Tensile strength	130	120	daN/5cm	NF EN ISO 1421
Tear strength	30	25	daN	DIN 53.363
Adhesion	7		daN/5cm	NF EN ISO 2411
Cold resistance	-30		°C	NF EN 1876-2
Warm resistance	70		°C	(24h)

Values may vary in a tolerance of +/-10%.

Specification maybe modified and are subject to manufacturer's requisites.

Product compatibility to the application is reserved to the users' appraisal.

The buyer of our products is responsible for checking the validity of the above data.

SYSTEM
LOWICK



RESOURCE

REACH
COMPLIANCE

MADE IN
FRANCE



DICKSON COATINGS
415, avenue de Savoie
F-38110 Saint-Clair-de-la-Tour
Tel. (+33) 04 74 83 51 00
Fax (+33) 04 74 83 51 01
www.dickson-coatings.com



GLEN RAVEN™

Glen Raven™ is a trademark
and Dickson® is a registered
trademark of Glen Raven, Inc.