

BLOCKLIGHT

Technical sheet

USES

Recommended use	Terrace awnings, Pergolas, Awnings, Small structures, Glamping, Sail shade
Comments	100% OPAQUE

CHARACTERISTICS	VALUES		UNITS	STANDARDS
	WARP	WEFT		

GENERAL CHARACTERISTICS

Base cloth	550 dTex PES HT			
Coating	PVC Lowick coating both side			
Finish	Cleangard lacquer both sides			
Weight	640		g/m ²	ISO 3801
Width	300	300	cm	
Roll length	30	60	ml	

FABRIC RESISTANCE

Tensile strength	150	150	daN/5cm	NF EN ISO 1421
Tear strength	15	15	daN	DIN 53.363
Adhesion	7		daN/5cm	NF EN ISO 2411
Elongation under load	<1	<3	%	NF EN 15619
Residual deformation	<0.4	<0.8	%	NF EN 15619
Temperature resistance	-30		C°	NF EN 1876-2
Temperature resistance	70		C°	(24h)
Fire resistance	M2			NF P 92 503

Specification maybe modified and are subject to manufacturer's requisites.
Values may vary in a tolerance of +/-10%.



DICKSON COATINGS
415, avenue de Savoie
F-38110 Saint-Clair-de-la-Tour
Tel. (+33) 04 74 83 51 00
Fax (+33) 04 74 83 51 01
www.dickson-coatings.com



GLEN RAVEN™

Glen Raven™ is a trademark
and Dickson® is a registered
trademark of Glen Raven, Inc.

**5 ANS
YEARS**

GARANTIE - WARRANTY

**SYSTEM
LOWICK**

**FINITION
CLEANGARD**



RESOURCE

**REACH
COMPLIANCE**

**MADE IN
FRANCE**