

# BLOCKLIGHT

## Technical sheet

### USES

Recommended use	Terrace awnings, Pergolas, Awnings, Small structures, Glamping, Sail shade
Comments	100% OPAQUE

CHARACTERISTICS	VALUES		UNITS	STANDARDS
	WARP	WEFT		

### GENERAL CHARACTERISTICS

Base cloth	550 dTex PES HT 495 den			
Coating	PVC Lowick coating both side			
Finish	Cleangard lacquer both sides			
Weight	640		g/m <sup>2</sup>	ISO 3801
Width	300	300	cm	
Roll length	30	60	ml	

### FABRIC RESISTANCE

Tensile strength	150	150	daN/5cm	NF EN ISO 1421
Tear strength	15	15	daN	DIN 53.363
Adhesion	7		daN/5cm	NF EN ISO 2411
Elongation under load	<1	<3	%	NF EN 15619
Residual deformation	<0.4	<0.8	%	NF EN 15619
Cold resistance	-30		°C	NF EN 1876-2
Warm resistance	70		°C	(24h)
Fire resistance	M2			NF P 92 503

Values may vary in a tolerance of +/-10%.  
Specification maybe modified and are subject to manufacturer's requisites.  
Product compatibility to the application is reserved to the users' appraisal.  
The buyer of our products is responsible for checking the validity of the above data.



**DICKSON COATINGS**  
415, avenue de Savoie  
F-38110 Saint-Clair-de-la-Tour  
Tel. (+33) 04 74 83 51 00  
Fax (+33) 04 74 83 51 01  
[www.dickson-coatings.com](http://www.dickson-coatings.com)



**GLEN RAVEN™**

Glen Raven™ is a trademark  
and Dickson® is a registered  
trademark of Glen Raven, Inc.

**5 ANS  
YEARS**  
GARANTIE - WARRANTY

**SYSTEM  
LOWICK**

**FINITION  
CLEANGARD**



**RESOURCE**

**REACH**  
COMPLIANCE

**MADE IN  
FRANCE**