

DICRISTAL 80

Technical sheet

USES

Recommended use

Flexible windows

CHARACTERISTICS	VALUES		UNITS	STANDARDS
	WARP	WEFT		

GENERAL CHARACTERISTICS

Thickness	0.8		mm	ISO 5084
Coating	PVC			
Finish	Transparent Anti UV			
Weight	1000		g/m ²	ISO 3801
Width	140		cm	
Roll length	20		ml	

FABRIC RESISTANCE

Tensile strength	210	190	Kg/cm ²	ASTM D 882
Tear strength	9	8	Kg/mm	ASTM D 1004
Elongation at break	410	550	%	ASTM D 882
Cold resistance	-20		°C	ASTM D 1790
Warm resistance	50		°C	(24h)

Values may vary in a tolerance of +/-10%.

Specification maybe modified and are subject to manufacturer's requisites.

Product compatibility to the application is reserved to the users' appraisal.

The buyer of our products is responsible for checking the validity of the above data.



DICKSON COATINGS
 415, avenue de Savoie
 F-38110 Saint-Clair-de-la-Tour
 Tel. (+33) 04 74 83 51 00
 Fax (+33) 04 74 83 51 01
www.dickson-coatings.com



GLEN RAVEN™

Glen Raven™ is a trademark
 and Dickson® is a registered
 trademark of Glen Raven, Inc.

