

# ECOLAC 640

## Technical sheet

### USES

Recommended use	Over top covers
Comments	PVC is composed of recycled paste (top-side grey 7196 : RAL 7037, and the reverse-side can vary)

CHARACTERISTICS	VALUES		UNITS	STANDARDS
	WARP	WEFT		

### GENERAL CHARACTERISTICS

Base cloth	1100 dTex PES HT 990 den			
Coating	PVC Lowick coating one side			
Finish	Cleangard lacquer both sides			
Weight	640		g/m <sup>2</sup>	ISO 3801
Width	300 300		cm	
Roll length	60 250		ml	

### FABRIC RESISTANCE

Tensile strength	220	210	daN/5cm	NF EN ISO 1421
Tear strength	30	25	daN	DIN 53.363
Adhesion	8		daN/5cm	NF EN ISO 2411
Cold resistance	-30		°C	NF EN 1876-2
Warm resistance	70		°C	(24h)
Fire resistance	< 100		mm/min	DIN 75 200

Values may vary in a tolerance of +/-10%.

Specification maybe modified and are subject to manufacturer's requisites.

Product compatibility to the application is reserved to the users' appraisal.

The buyer of our products is responsible for checking the validity of the above data.

SYSTEM  
LOWICK

FINITION  
CLEANGARD



RESOURCE

REACH  
COMPLIANCE

MADE IN  
FRANCE



**DICKSON COATINGS**  
415, avenue de Savoie  
F-38110 Saint-Clair-de-la-Tour  
Tel. (+33) 04 74 83 51 00  
Fax (+33) 04 74 83 51 01  
[www.dickson-coatings.com](http://www.dickson-coatings.com)



GLEN RAVEN™

Glen Raven™ is a trademark  
and Dickson® is a registered  
trademark of Glen Raven, Inc.