

JET 250

Technical sheet

USES

Recommended use	Banners, Signage, Ecologic banners
Printing	Printable side : outside
Ink	Solvent, Eco-solvent, UV, Latex Ink

CHARACTERISTICS	VALUES		UNITS	STANDARDS
	WARP	WEFT		

GENERAL CHARACTERISTICS

Thickness	0.27		mm	ISO 5084
Base cloth	550 dTex PES HT 495 den			
Coating	EverGreen coating			
Finish	Inkjet lacquer one side			
Weight	200		g/m ²	ISO 3801
Translucency	25		%	XPT 54199
Width	106	320	cm	
Roll length	50	60	ml	

FABRIC RESISTANCE

Tensile strength	200	150	daN/5cm	NF EN ISO 1421
Tear strength	30	25	daN	DIN 53.363

Values may vary in a tolerance of +/-10%.

Specification maybe modified and are subject to manufacturer's requisites.

Product compatibility to the application is reserved to the users' appraisal.

The buyer of our products is responsible for checking the validity of the above data.



DICKSON COATINGS
415, avenue de Savoie
F-38110 Saint-Clair-de-la-Tour
Tel. (+33) 04 74 83 51 00
Fax (+33) 04 74 83 51 01
www.dickson-coatings.com



GLEN RAVEN™

Glen Raven™ is a trademark and Dickson® is a registered trademark of Glen Raven, Inc.



**PVC
FREE**

