

JET 400

Technical sheet

USES

Recommended use	Banners, Signage, Pole banners
Printing	Printable side : outside
Ink	Solvent, Eco-solvent, UV, Latex Ink

CHARACTERISTICS	VALUES		UNITS	STANDARDS
	WARP	WEFT		

GENERAL CHARACTERISTICS

Thickness	0.34		mm	ISO 5084
Base cloth	1100 dTex PES HT 990 den			
Coating	Lowick			
Finish	Inkjet lacquer one side			
Weight	370		g/m ²	ISO 3801
Translucency	15		%	XPT 54199
Width	106	320	320	cm
Roll length	50	50	100	ml

FABRIC RESISTANCE

Tensile strength	210	200	daN/5cm	NF EN ISO 1421
Tear strength	25	20	daN	DIN 53.363
Adhesion	7		daN/5cm	NF EN ISO 2411
Cold resistance	-30		°C	NF EN 1876-2
Warm resistance	70		°C	(24h)

Values may vary in a tolerance of +/-10%.
Specification maybe modified and are subject to manufacturer's requisites.
Product compatibility to the application is reserved to the users' appraisal.
The buyer of our products is responsible for checking the validity of the above data.



DICKSON COATINGS
415, avenue de Savoie
F-38110 Saint-Clair-de-la-Tour
Tel. (+33) 04 74 83 51 00
Fax (+33) 04 74 83 51 01
www.dickson-coatings.com



GLEN RAVEN™

Glen Raven™ is a trademark
and Dickson® is a registered
trademark of Glen Raven, Inc.



**SYSTEM
LOWICK**



RESOURCE

**REACH
COMPLIANCE**

**MADE IN
FRANCE**