

JET 520

Technical sheet

USES

Recommended use	Banners, P.O.S, Signage, Stand, Separation curtains
Printing	Printable side : outside
Ink	Solvent, Eco-solvent, UV, Latex Ink

CHARACTERISTICS	VALUES		UNITS	STANDARDS
	WARP	WEFT		

GENERAL CHARACTERISTICS

Thickness	0.45	mm	ISO 5084
Base cloth	1100 dTex PES HT 990 den		
Coating	PVC Lowick coating one side		
Finish	Inkjet lacquer one side		
Weight	550	g/m ²	ISO 3801
Translucency	6	%	XPT 54199
Width	106 137 162 250 320 320	cm	
Roll length	30 30 30 60 30 60	ml	

FABRIC RESISTANCE

Tensile strength	210	200	daN/5cm	NF EN ISO 1421
Tear strength	25	20	daN	DIN 53.363
Adhesion	7		daN/5cm	NF EN ISO 2411
Cold resistance	-30		°C	NF EN 1876-2
Warm resistance	70		°C	(24h)
Fire resistance	M1			NF P 92 503
	B-S2-D0			Euroclasses EN 13501-1

Values may vary in a tolerance of +/-10%.
Specification maybe modified and are subject to manufacturer's requisites.
Product compatibility to the application is reserved to the users' appraisal.
The buyer of our products is responsible for checking the validity of the above data.

SYSTEM
LOWICK



RESOURCE

REACH
COMPLIANCE

MADE IN
FRANCE



DICKSON COATINGS
415, avenue de Savoie
F-38110 Saint-Clair-de-la-Tour
Tel. (+33) 04 74 83 51 00
Fax (+33) 04 74 83 51 01
www.dickson-coatings.com



GLEN RAVEN™

Glen Raven™ is a trademark
and Dickson® is a registered
trademark of Glen Raven, Inc.