

JET TEX WALL

Technical sheet

USES

Recommended use	Wall covering, Shop design
Printing	Printable side : outside
Ink	Solvent, Eco-solvent, UV, Latex Ink

CHARACTERISTICS	VALUES		UNITS	STANDARDS
	WARP	WEFT		

GENERAL CHARACTERISTICS

Thickness	0.27	mm	ISO 5084
Base cloth	Polyester		
Coating	EverGreen coating		
Finish	Inkjet lacquer one side		
Weight	300	g/m ²	ISO 3801
Translucency	14	%	XPT 54199
Width	102	cm	
Roll length	30	ml	

FABRIC RESISTANCE

Tensile strength	120	70	daN/5cm	NF EN ISO 1421
Tear strength	12	9	daN	DIN 53.363
Fire resistance	B-s2-d0			Euroclasses EN 13501-1
	NFPA 701			NFPA 701
	ASTM E 84			ASTM E 84

Values may vary in a tolerance of +/-10%.
 Specification maybe modified and are subject to manufacturer's requisites.
 Product compatibility to the application is reserved to the users' appraisal.
 The buyer of our products is responsible for checking the validity of the above data.



DICKSON COATINGS
 415, avenue de Savoie
 F-38110 Saint-Clair-de-la-Tour
 Tel. (+33) 04 74 83 51 00
 Fax (+33) 04 74 83 51 01
www.dickson-coatings.com



GLEN RAVEN™

Glen Raven™ is a trademark and Dickson® is a registered trademark of Glen Raven, Inc.



EverGreen
FABRICS

**PVC
FREE**

