

# LAC 680

## Technical sheet

### USES

Recommended use

Truck roofing

CHARACTERISTICS	VALUES		UNITS	STANDARDS
	WARP	WEFT		

### GENERAL CHARACTERISTICS

Base cloth	1100 dTex PES HT 990 den					
Coating	PVC Lowick coating both side					
Finish	Cleangard lacquer both sides					
Weight	680				g/m <sup>2</sup>	ISO 3801
Width	250 320	250 320	285 320	285 300	300 300	cm
Roll length	60 60	250 250	60 250	250 60	250 250	ml

### FABRIC RESISTANCE

Tensile strength	220	210	daN/5cm	NF EN ISO 1421
Tear strength	30	25	daN	DIN 53.363
Adhesion	8		daN/5cm	NF EN ISO 2411
Cold resistance	-30		°C	NF EN 1876-2
Warm resistance	70		°C	(24h)
Fire resistance	< 100		mm/min	DIN 75 200

Values may vary in a tolerance of +/-10%.

Specification maybe modified and are subject to manufacturer's requisites.

Product compatibility to the application is reserved to the users' appraisal.

The buyer of our products is responsible for checking the validity of the above data.



**DICKSON COATINGS**  
415, avenue de Savoie  
F-38110 Saint-Clair-de-la-Tour  
Tel. (+33) 04 74 83 51 00  
Fax (+33) 04 74 83 51 01  
[www.dickson-coatings.com](http://www.dickson-coatings.com)



Glen Raven™ is a trademark  
and Dickson® is a registered  
trademark of Glen Raven, Inc.