

LAC 900

Technical sheet

USES

Recommended use Tarpaulins for agriculture, Truck side curtains, Over top covers, Flexible doors

Comments Complies with : EN 12641-2

CHARACTERISTICS	VALUES		UNITS	STANDARDS
	WARP	WEFT		

GENERAL CHARACTERISTICS

Base cloth	1100 dTex PES HT 990 den			
Coating	PVC Lowick coating both side			
Finish	Cleangard lacquer both sides			
Weight	900		g/m ²	ISO 3801
Width	300	300	300	cm
Roll length	30	60	200	ml

FABRIC RESISTANCE

Tensile strength	400	400	daN/5cm	NF EN ISO 1421
Tear strength	60	50	daN	DIN 53.363
Adhesion	10		daN/5cm	NF EN ISO 2411
Puncture resistance	8		kN	NF EN 12236
Cold resistance	-30		°C	NF EN 1876-2
Warm resistance	70		°C	(24h)
Fire resistance	<100		mm/min	DIN 75 200

Values may vary in a tolerance of +/-10%.

Specification maybe modified and are subject to manufacturer's requisites.

Product compatibility to the application is reserved to the users' appraisal.

The buyer of our products is responsible for checking the validity of the above data.

SYSTEM
LOWICK

FINITION
CLEANGARD



RESOURCE

REACH
COMPLIANCE

MADE IN
FRANCE



DICKSON COATINGS
415, avenue de Savoie
F-38110 Saint-Clair-de-la-Tour
Tel. (+33) 04 74 83 51 00
Fax (+33) 04 74 83 51 01
www.dickson-coatings.com



GLEN RAVEN™

Glen Raven™ is a trademark
and Dickson® is a registered
trademark of Glen Raven, Inc.