

UNILAC

Technical sheet

USES

Recommended use

Trailers, Tarpaulins for agriculture, Over top covers, Covers and lagging

CHARACTERISTICS	VALUES		UNITS	STANDARDS
	WARP	WEFT		

GENERAL CHARACTERISTICS

Base cloth	1100 dTex PES HT 990 den			
Coating	PVC Lowick coating one side			
Finish	Cleangard lacquer both sides			
Weight	540		g/m ²	ISO 3801
Width	300	300	cm	
Roll length	60	250	m	

FABRIC RESISTANCE

Tensile strength	220	210	daN/5cm	NF EN ISO 1421
Tear strength	25	20	daN	DIN 53.363
Adhesion	8		daN/5cm	NF EN ISO 2411
Cold resistance	-30		°C	NF EN 1876-2
Warm resistance	70		°C	(24h)
Fire resistance	< 100		mm/min	DIN 75 200

Values may vary in a tolerance of +/-10%.

Specification maybe modified and are subject to manufacturer's requisites.

Product compatibility to the application is reserved to the users' appraisal.

The buyer of our products is responsible for checking the validity of the above data.

SYSTEM
LOWICK

FINITION
CLEANGARD



RESOURCE

REACH
COMPLIANCE

MADE IN
FRANCE



DICKSON COATINGS
415, avenue de Savoie
F-38110 Saint-Clair-de-la-Tour
Tel. (+33) 04 74 83 51 00
Fax (+33) 04 74 83 51 01
www.dickson-coatings.com



GLEN RAVEN™

Glen Raven™ is a trademark
and Dickson® is a registered
trademark of Glen Raven, Inc.