

# WINDTEX 70

## Technical sheet

### USES

Recommended use Windbreakers, Meshes, Over top covers

CHARACTERISTICS	VALUES		UNITS	STANDARDS
	WARP	WEFT		

### GENERAL CHARACTERISTICS

Base cloth	1100 dTex PES HT 990 den				
Coating	PVC Lowick coating both side				
Finish	2 sides lacquered				
Weight	460			g/m <sup>2</sup>	ISO 3801
Wind efficiency	72			%	XP G39-100-3
Multiplier coefficient	1.4				XP G39-100-1
Porosity	36			%	
Width	300	300	300	cm	
Roll length	30	60	250	ml	

### FABRIC RESISTANCE

Tensile strength	275	275		daN/5cm	NF EN ISO 1421
Tear strength	45	50		daN	DIN 53.363
Adhesion	9			daN/5cm	NF EN ISO 2411
Cold resistance	-30			°C	NF EN 1876-2
Warm resistance	70			°C	(24h)

Values may vary in a tolerance of +/-10%.  
Specification maybe modified and are subject to manufacturer's requisites.  
Product compatibility to the application is reserved to the users' appraisal.  
The buyer of our products is responsible for checking the validity of the above data.

SYSTEM  
LOWICK



RESOURCE

REACH  
COMPLIANCE

MADE IN  
FRANCE



**DICKSON COATINGS**  
415, avenue de Savoie  
F-38110 Saint-Clair-de-la-Tour  
Tel. (+33) 04 74 83 51 00  
Fax (+33) 04 74 83 51 01  
[www.dickson-coatings.com](http://www.dickson-coatings.com)



GLEN RAVEN™

Glen Raven™ is a trademark  
and Dickson® is a registered  
trademark of Glen Raven, Inc.